

PRODUCT DATASHEET

POLYPROPYLENE

RE425MO

POLYPROPYLENE RANDOM COPOLYMER FOR INJECTION MOULDING AND ISBM

DESCRIPTION

RE425MO is a versatile designed transparent polypropylene random copolymer with medium melt flow rate intended for injection moulding and injection stretch blow moulding.

RE425MO is suitable for high speed injection moulding with excellent clarifier and demoulding properties. Articles produced from this product have excellent transparency, excellent impact strength at ambient and refrigerator temperatures, good organoleptic properties, low blooming, good denesting performance and excellent hinge properties.

APPLICATIONS

Lids
Houseware containers
Customized / hinged closures

Food storage containers
Sports and drinking bottles
Transparent pails

SPECIAL FEATURES

Excellent impact performance
Very good gloss and transparency

Low blooming
Excellent hinge properties

PHYSICAL PROPERTIES

Property	Typical Value	Test Method
Density	900-910kg/m ³	ISO 1183
Melt Flow Rate (230°C/2.16kg)	14g/10min	ISO 1133
Flexural Modulus	950MPa	ISO 178
Charpy Impact Strength, notched (23°C)	7kJ/m ²	ISO 179/1eA
IZOD Impact Strength, notched (23°C)	75J/m	ASTM D256
Haze(2mm)	<20%	ASTM D1003

*Data should not be used for specification work

**Measured on injection moulded specimens acc. to ISO 19069-2

***Measured on injection moulded specimens, conditioned at 23°C and 50% Rel. Humidity

PROCESSING CONDITIONS

RE425MO is easy to process with standard injection moulding -and injection stress blow moulding machines.

Following parameters should be used as guidelines:

Melt temperature: 220 - 260°C
Holding pressure: 200 - 500bar
Mould temperature: 30 - 40°C
Injection speed: High
Shrinkage 1 - 2%, depending on wall thickness and moulding parameters

STORAGE

RE425MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product. More information on storage can be found in Safety Information Sheet (SIS) for this product

SAFETY

The product is not classified as a hazardous preparation.

Please see our Safety Information Sheet (SIS) for details on various aspects of safety, recovery and disposal of the product, for more information contact your Borouge representative.

RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Information Sheet

Statement on chemicals, regulations and standards

Statement on compliance to food contact regulations

DISCLAIMER

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borouge makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose.

The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borouge products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

September 2021